

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORLED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

WEST☐ **Generate Collection** **Print**

L2: Entry 8 of 10

File: DWPI

Sep 9, 1987

DERWENT-ACC-NO: 1987-251510

DERWENT-WEEK: 198736

COPYRIGHT 2002 DERWENT INFORMATION LTD

TITLE: Transparent aq. tin solns. - prepd. by reacting tin carboxylate with hydrogen peroxide

INVENTOR: KOBASHI, T

PATENT-ASSIGNEE:

ASSIGNEE

CODE

JAPAN EXLAN CO LTD

JAPE

PRIORITY-DATA: 1986JP-0026241 (February 8, 1986), 1986JP-0026239 (February 8, 1986), 1986JP-0026240 (February 8, 1986)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
EP 235968 A	September 9, 1987	E	015	
DE 3765556 G	November 22, 1990		000	
EP 235968 B	October 17, 1990		000	
JP 62184713 A	August 13, 1987		000	
JP 62184714 A	August 13, 1987		000	
JP 62187113 A	August 15, 1987		000	
JP 93046645 B	July 14, 1993		002	H01B013/00
JP 93046646 B	July 14, 1993		003	H01B013/00
JP 94017229 B2	March 9, 1994		003	C01G019/02
KR 9000082 B	January 19, 1990		000	
US 4873352 A	October 10, 1989		004	

DESIGNATED-STATES: DE FR GB DE FR GB

CITED-DOCUMENTS: 1.Jnl.Ref; AU 513419 ; GB 1517341 ; SU 1033440 ; SU 541849

APPLICATION-DATA:

PUB-NO	APPL-DATE	APPL-NO	DESCRIPTOR
EP 235968A	February 6, 1987	1987EP-0301058	
JP62184713A	February 8, 1986	1986JP-0026239	
JP62184714A	February 8, 1986	1986JP-0026240	
JP62187113A	February 8, 1986	1986JP-0026241	
JP93046645B	February 8, 1986	1986JP-0026239	
JP93046645B		JP62184713	Based on
JP93046646B	February 8, 1986	1986JP-0026240	
JP93046646B		JP62184714	Based on
JP94017229B2	February 8, 1986	1986JP-0026241	
JP94017229B2		JP62187113	Based on
US 4873352A	February 4, 1987	1987US-0011863	

INT-CL (IPC): C01G 19/02; C03C 17/23; C03C 17/25; C07F 7/22; G02F 1/1343; G09F 9/30; H01B 1/08; H01B 13/00; H01L 31/042

ABSTRACTED-PUB-NO: EP 235968A
BASIC-ABSTRACT:

Transparent aq. solns. of Sn cpds. are prep'd. by reacting an Sn carboxylate (I) with H₂O₂ in an aq. medium, using at least 1.5 mole H₂O₂ per mole of (I).

Pref. the solns. also contain a dopant (esp. Sb₂O₃) in an amt. of 0.01-0.35 mole per mole of (I). The solns. are converted to transparent SnO₂ by calcining at a temp. above 400 deg.C.

USE/ADVANTAGE - The solns. are useful for prodn. of transparent conductive films of SnO₂, e.g. useful as transparent electrodes, heating elements, resistors or IR reflectors. The solns. give SnO₂ with good transparency, uniformity, compactness and conductivity.
ABSTRACTED-PUB-NO:

EP 235968B
EQUIVALENT-ABSTRACTS:

A transparent aq. tin cpd. soln. obtd. by reacting a tin carboxylate with hydrogen peroxide in the molar ratio of 1:1:5 or above in an aq. medium. (7pp)

US 4873352A

A transparent aqueous tin compound soln. is prepared by preparing an aqueous soln. containing up to 20

tin oxalate and then adding 1.6-2.2 mol. of hydrogen peroxide. The reaction is conducted at a temp. between ambient temp. and the boiling point for the soln. The mixture being stirred for 5-20 mins.

ADVANTAGE - The soln. can be applied to suitable substrates and calcined to give transparent electrically conductive coatings of tin oxide. (4pp)a

CHOSEN-DRAWING: Dwg.0/0

TITLE-TERMS: TRANSPARENT AQUEOUS TIN SOLUTION PREPARATION REACT TIN
CARBOXYLATE HYDROGEN PEROXIDE

DERWENT-CLASS: E32 L03 P81 P85 U11 U14 X12

CPI-CODES: E35-H; L01-L04; L03-A02A; L03-H04A;

EPI-CODES: U11-C05C6; U11-C18D; U14-H01E; U14-H01F; X12-D01B;
X12-D02A;

CHEMICAL-CODES:

Chemical Indexing M3 *01*

Fragmentation Code

A350 A940 C108 C550 C730 C801 C802 C803 C804 C805

C807 M411 M720 M903 M904 M910 N411 N421 N514 Q010

Q452 Q454 R043

Specific Compounds

01531P

Registry Numbers

87140 1286M

UNLINKED-DERWENT-REGISTRY-NUMBERS: 1531P; 1732S

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C1987-106425

Non-CPI Secondary Accession Numbers: N1987-188218

⑫

EUROPEAN PATENT APPLICATION

⑰ Application number: **87301058.1**

⑮ Int. Cl.: **C 03 C 17/23, C 03 C 17/25**

⑱ Date of filing: **06.02.87**

⑳ Priority: **08.02.86 JP 26239/86**
08.02.86 JP 26240/86
08.02.86 JP 26241/86

㉑ Applicant: **JAPAN EXLAN COMPANY, LTD., 2-8,**
Dojimahama-2-chome Kita-ku, Osaka-shi
Osaka 530 (JP)

㉒ Date of publication of application: **09.09.87**
Bulletin 87/37

㉓ Inventor: **Kobashi, Toshiyuki, 1-6 Saidaiji Kami 3-chome,**
Okayama (JP)
Inventor: **Naka, Hideo, 794-14, Kanada, Okayama (JP)**

㉔ Designated Contracting States: **DE FR GB**

㉕ Representative: **Bass, John Henton et al, REDDIE &**
GROSE 16 Theobalds Road, London WC1X 8PL (GB)

㉖ **Transparent aqueous tin compound solution and method of producing transparent conductive tin oxide.**

㉗ By reacting a tin carboxylate with hydrogen peroxide at a particular ratio in an aqueous medium, this invention provides a transparent aqueous tin compound solution which can finally form, in an industrially advantageous manner, tin oxide having excellent transparency, uniformity, compactness, conductivity, etc.

EP 0 235 968 A1

TRANSPARENT AQUEOUS TIN COMPOUND SOLUTION AND METHOD
OF PRODUCING TRANSPARENT CONDUCTIVE TIN OXIDE

Background of the Invention

a) Field of the Invention

This invention relates to a transparent aqueous tin compound solution suitable for forming transparent conductive tin oxide and to a method of producing transparent conductive tin oxide using said aqueous solution.

b) Description of the Prior Art

In recent years, accompanied with the remarkable development in the field of electro-optical elements, attention is paid to transparent conductive membranes of the type of SnO_2 or In_2O_3 . They are actively developed, for example, as transparent electrodes of various optical devices such as those of electro-luminescence, liquid crystals, image accumulation devices, etc.; as heating elements or resistors utilizing their heat resistance and anti-abrasion properties; as solar cells utilizing their high conductivity; or as selective permeable membranes for use in solar heat electricity generation utilizing their high reflexivity in infrared.

Among the methods of forming these transparent conductive membranes are known:

0235968

- (1) chemical vapor deposition method,
- (2) vacuum evaporation method,
- (3) sputtering method,
- (4) coating method.

All of the above-mentioned methods (1)-(3) use complicated apparatus and are inferior in operability. In addition, they usually necessitate an etching step after membrane formation, to form a pattern.

In the method (4) also, when using an inorganic salt such as SnCl_4 , for example, since hydrogen chloride or other chloride gases are generated upon heat decomposition, severe corrosion of the apparatus takes place. Also, the chlorine remaining in the membrane may become a cause of impairing the conductivity. There are also methods of using organic acid salts such as octyl acid tin salt or an organic complex. But in these methods, there are problems such that the uniformity of the membrane is impaired upon heat decomposition or gelation of the coating liquid takes place. Moreover, they have defects such that the formed membrane is uneven, cloudy and is liable to get hurt.

We, the inventors, taking the above-mentioned problems of the prior art into account, carried on further studies, and as a result, we attained this invention.

The object of this invention is to provide a transparent aqueous tin compound solution which has no restriction or problem on the apparatus, has high applicability, and can finally form tin oxide having excellent transparency, uniformity, compactness and conductivity, in an industrially advantageous manner, and to provide a method of producing

transparent conductive tin oxide by using said aqueous solution.

Summary of the Invention

The above-mentioned object of this invention is attained by a transparent aqueous tin compound solution formed by reacting a tin carboxylate with hydrogen peroxide in molar ratio of 1:1.5 or above, in an aqueous medium, and by calcinating said aqueous solution at a temperature above 400°C.

Detailed Description of the Invention

As the tin carboxylates used in this invention may be mentioned for example, stannous formate, stannous acetate, stannous oxalate, stannous tartrate, etc. However, for the attainment of this invention, stannous oxalate is preferable.

The quantity of hydrogen peroxide should be 1.5 mol or more, preferably within the range of from 1.6 to 2.2 mol for one mol of the tin salt. When the quantity goes beyond the lower limit of the range, the compactness and conductivity of the finally obtained tin oxide will be lowered, and also no improvement in performance will be observed even if it is used in a quantity more than the actual necessity.

As the aqueous medium, water is usually used, but an amount of a water-miscible organic solvent may be used together in a range in which a viscosity rise or gelation of the reaction-produced solution will not occur.

The method of producing the aqueous solution of the object is to add a tin carboxylate to an aqueous medium under stirring and then add a prescribed quantity of hydrogen peroxide.

Even if the reaction is initiated at room temperature, there are cases where boiling may take place by the reaction heat. Therefore, when the reaction is conducted at a temperature below the boiling point, it is desirable that the concentration of the tin carboxylate should be determined generally below 20 weight %, preferably below 18 weight %.

In order to provide a transparent aqueous solution in which a dopant is uniformly contained and which can finally form tin oxide having excellent transparency, uniformity, compactness, conductivity, etc., it is desirable to make a dopant coexist in the reaction system. Among such dopants may be mentioned compounds containing elements of Ib Group such as Cu, Ag, Au; those of IIIa Group such as Ce, Eu; those of Va Group such as V, Nb, Ta; those of Vb Group such as As, Sb, Bi; those of VIa Group such as Cr, Mo, W; those of VIIa Group such as Re; those of VIII Group such as Ru, Rh, Pd, Os, Ir, Pt; and fluorine. Among others, compounds containing elements selected from Ib, Va, Vb, VIa, VIII Groups and fluorine are preferable. Especially, coexistence of antimony oxides such as Sb_2O_3 , Sb_2O_4 , Sb_6O_{13} , etc. in the reaction system makes it possible to form a uniform, reaction-produced transparent aqueous solution, and finally makes it possible to provide tin oxide having very good conductivity. Therefore, such coexistence is desirable.

Desirably, the quantity of such a dopant to be used should be determined to be in the range of from 0.01 to 0.35 mol, preferably from 0.03 to 0.25 mol, for one mol of tin carboxylate.

In this way, a transparent aqueous solution of the tin compound showing a pH below 1.5 can be obtained in a reaction time usually from 5 to 50 minutes. The aqueous solution without any treatment, or after suitable concentration or addition of a dopant, can be subjected to shaping, such as formation of a membrane on a substrate such as a glass plate, or after being made into powder by a suitable operation such as spray drying, it can be calcinated to produce conductive tin oxide.

The calcination conditions employed are generally temperatures from 400°C to 1000°C, preferably from 500° to 800°C, for 0.5 to 5 hours, preferably for 1 to 3 hours.

As mentioned above, from the transparent aqueous tin compound solution of this invention, it is possible to form tin oxide of excellent transparency, uniformity, compactness, conductivity, etc. in any form such as powder, membrane, etc., without using any complicated apparatus or without any problem of inferior operability. These are the characteristic advantages of this invention.

Thus, the transparent aqueous tin compound solution and the tin oxide produced from said aqueous solution are used

in the use fields of fillers, paints, membranes, etc. for which conductivity is especially required, or in various use fields such as transparent heating elements, gas sensors, infrared reflexing membranes, lithium ion selective adsorption agents, catalysts, flame-retardants, etc.

Examples

This invention will be explained in detail by way of Examples in the following. In the Examples, the conductivity was obtained as follows:

The reaction-produced liquid is spray-dried and pulverized by means of a ball mill into particles having an average particle diameter of about 5 μ . The particles are calcinated at 500°C for 3 hours to produce a sample. One gram of the sample is packed into an electrode for solid matter use (SE-70 type), produced by Ando Denki Co. Then the electrode spring is set, and by means of a LCR-meter (AX-221 type) produced by ADEX Co. Ltd., the electric resistance (Ω) is obtained.

The bulk density (g/ml) was obtained as follows:

A sample of 10 g is packed into a cell (inner diameter: 20.5 mm; length: 50 mm). The compressed heights (h mm) are obtained under various loads of the electrode piston (inner diameter: 20 mm, length: 60 mm).

The resistivity (Ω .cm) was obtained by measuring the electric resistance R (Ω) using a four probe ohm meter (3224

type) produced by Hioki Denki Co. Ltd.

Example 1

Stannous oxalate (SnC_2O_4) was added to water of room temperature and the mixture was stirred to form a slurry. An aqueous 35 weight % hydrogen peroxide solution was added to the slurry in the ratios shown in Table 1 below for one mol of SnC_2O_4 to react for 30 minutes, producing 5 kinds of transparent aqueous solutions (A-E). The concentration of SnC_2O_4 in each reaction system was determined at 15 weight %.

The pH value of each reaction-produced liquid as well as the bulk density and conductivity of the calcinated samples were measured. The results are shown together in Table 1.

Table 1

Sample	H_2O_2 (mol)	pH of the reaction- produced liquid	Calcinated sample	
			Bulk density (g/ml) *	Conductivity (k Ω)
A	1.0	1.7	2.4	1,600
B	1.3	1.7	2.4	1,400
C	1.6	0.8	3.2	160
D	2.0	0.6	3.4	150
E	2.2	0.6	3.3	150

* Values under the load of 1 t/cm²

From the above Table, it is clearly understood that by following this invention, it is possible to provide a transparent aqueous tin compound solution which can form tin oxide having high compactness and exhibiting excellent conductivity.

On the other hand, to a 15 weight % aqueous solution of stannic chloride, an aqueous ammonium solution was added so that the pH of the solution became 8, thereby to produce colloidal stannic hydroxide. The colloidal stannic hydroxide was evaluated in the same way as above. The bulk density was 2.2 g/ml and the conductivity was 1,700 kΩ.

Example 2

Five kinds of transparent aqueous solutions (F-J) were produced in the same way as Example 1 (D) except that amounts of Sb_2O_3 shown in Table 2 below were added for one mol of $SnCl_4$. The values of the conductivity of these solutions were measured, and the results are shown in Table 2.

Table 2

Sample	F	G	H	I	J
Quantity of Sb_2O_3 added (mol)	0.005	0.03	0.05	0.25	0.35
Conductivity Ω	135	3	1	3	30

The conductivity of the dispersion liquid obtained by adding 0.1 mol Sb_2O_3 to Example 1 (D) was 12 k Ω .

Example 3

Two kinds of transparent aqueous solutions (K and L) were produced by adding SnC_2O_4 to room temperature water and adding 1 mol or 2 mol of a 35 weight % aqueous H_2O_2 solution for 1 mol of SnC_2O_4 under stirring to react for 30 minutes.

Transparent aqueous solutions (M and N) were produced in the same way as above except that one mol of Sb_2O_3 for one mol of SnC_2O_4 was added together with SnC_2O_4 . The concentration of SnC_2O_4 in the reaction system was determined to be 15 weight % in each case.

After spray-drying the thus obtained aqueous solutions (K-N), the resulting solid matter was pulverized into particles of average particle diameter of about 5 μ by means of a ball mill. The particles were then calcinated in air at 500°C for 3 hours, thus producing 4 kinds of tin oxide powder (K-N). The bulk density and resistivity were measured under a load of 1 t/cm². The results are shown in Table 3.

Table 3

Sample	Quantity added for 1 mol of SnC_2O_4		Bulk density (g/ml)	Resis- tivity ($\Omega\cdot\text{cm}$)
	H_2O_2 (mol)	Sb_2O_3 (mol)		
K	1	0	2.4	4×10^2
L	2	0	3.4	5×10^1
M	1	0.1	2.4	8×10^{-1}
N	2	0.1	3.4	7×10^{-2}

It is understood from the above Table that by determining the quantity of H_2O_2 within the range of this invention, it is possible to improve the conductivity, and by adding a dopant the conductivity is remarkably elevated.

Example 4

Under various loads, measurement of bulk density and resistivity was made on Example 3 sample N and tin oxide conductive powder T-1 produced by Mitsubishi Metal Co.Ltd. The results are shown in Table 4.

Table 4

Load (t/cm ²)		1	2	3	4	5
Bulk density (g/ml)	Sample N	3.4	3.8	4.0	4.2	4.3
	T-1	2.2	2.7	3.3	3.9	4.3
Resistivity (Ω .cm)	Sample N	7×10^{-2}	4×10^{-2}	3.4×10^{-2}	3.2×10^{-2}	3.0×10^{-2}
	T-1	8×10^{-1}	7.5×10^{-1}	7×10^{-1}	7×10^{-1}	7.0×10^{-1}

It is clearly understood from the above Table that the product of this invention has excellent conductivity under every load.

Four kinds of tin oxide powder (O-R) were produced in the same way as Example 3 sample N except that the kind of dopant was varied.

The resistivity under the load of 1 t/cm² was measured for each sample. The results are shown in Table 5.

Table 5

Sample	Kind of dopant	Resistivity (Ω .cm)
O	SnF ₂	11
P	Cu(HCOO) ₂	34
Q	Nb ₂ O ₅	38
R	Ce ₂ (C ₂ O ₄) ₃	23
L	none	50

Example 6

Six kinds of tin oxide powder (S-X) were produced in the same way as Example 3 sample N except that the quantity of Sb₂O₃ was varied.

0235968

The values of resistivity of these samples under the load of 1 t/cm² are shown in Table 6.

Table 6

Sample	S	T	U	V	W	X
Quantity of Sb ₂ O ₃ added (mol)	0.01	0.03	0.05	0.25	0.35	0.4
Resistivity (Ω .cm)	7x10 ⁻¹	1x10 ⁻¹	8x10 ⁻²	5x10 ¹	2x10 ²	3x10 ³

Example 7

The transparent aqueous solution (N) of Example 3 was spinner coated at 3,000 rpm onto a quartz glass substrate, and was calcinated in air at 700°C for two hours to produce a transparent conductive membrane.

The properties of the membrane are shown in Table 7.

Table 7

Membrane thickness (Å)	Percent transmittance (%)	Surface resistivity (Ω / □)	Membrane surface
300	90	200	smooth, uniform

CLAIMS

1. A transparent aqueous tin compound solution obtained by reacting a tin carboxylate with hydrogen peroxide in the ratio of 1 : 1.5 or above in an aqueous medium.

2. The transparent aqueous solution as claimed in Claim 1 obtained by making coexist in the reaction system, a dopant of a quantity of from 0.01 to 0.35 mol for one mol of the tin carboxylate.

3. A method of producing a transparent conductive tin oxide characterized by reacting a tin carboxylate with hydrogen peroxide in the ratio of 1 : 1.5 or above in an aqueous medium, and calcinating the thus-obtained transparent aqueous solution at a temperature above 400°C.

4. The method as claimed in Claim 3 wherein a dopant is made to coexist in the reaction system in the ratio of from 0.01 to 0.35 mol for one mol of the tin carboxylate.



European Patent
Office

EUROPEAN SEARCH REPORT

0235968

Application Number

EP 87 30 1058

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
X	SU-A- 541 849 (T.F. DOBROXOTOVA) * Claims; column 1, lines 19-22; column 2, example 1; column 5, lines 26-34 *	1, 3	C 03 C 17/23 C 03 C 17/25
Y		2, 4	
Y	GB-A-1 517 341 (DAY SPECIALTIES CO.) * Claims 1, 8 *	2, 4	
A	CHEMICAL ABSTRACTS, vol. 99, no. 20, 1983, page 129, abstract no. 160791f, Columbus, Ohio, US; & SU-A-1 033.440 (V.P. KARLOV et al.) 07-08-1983 * Whole abstract *	1	
A	AU-A- 513 419 (MATSUSHITA) * Claim 1 *	1-4	C 03 C C 01 G
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
Place of search THE HAGUE		Date of completion of the search 13-05-1987	Examiner BOUTRUCHE J.P.E.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO Form 1503 03/82